

This certificate is an example. A complete certificate containing lot-specific information, such as concentration and volume, will be shipped with your purchase.



## PAN-Chromeo™ 546 Tensidic-blocked (PAN Nanoparticles)

**Catalog No:** 15232, 16232

**Lot No:** Not Available

### Chemical Properties:

Contents: 5 ml (Cat # 15232) or 10 ml (Cat # 16232) aqueous suspension of PAN-Chromeo 546 Tensidic blocked, 0.5 % (w/w) in 10 mM MOPS + 0.5 % (w/w) Tween, pH 7, 15 mM sodium azide.

### Fluorescent Properties:

PAN-Particles are based on a novel polymer, which form lattices with a reduced oxygen permeability and results in a very good protection of the incorporated dye against other environmental effects. The combination of this new polymer with the Chromeo-dyes results in novel nanoparticles with high fluorescent intensities. The particles are smaller than 50 nm, the main fraction is about 30 nm in diameter. The surface is carboxy-modified, has additional sulfo-groups and is blocked with Tween. PAN-Nanoparticles are “loaded” with the lipophilic-form of Chromeo 546, showing similar fluorescent properties as the yellow-orange Cy3 dye. Filters designed for Cy3 can be used with Chromeo 546 carboxylated particles.

Excitation Max: 520, 540 nm

Emission Max: 577 nm

Diameter (average): 30 nm

Delivery form: 0.5 % (w/w) in buffer

### Quality Control:

The particles have been quality tested by spectro-photometrical evaluation and by determining the solid residue after lyophilization.

### Storage:

To ensure stability, the aqueous suspension should be stored at 4°C in the dark. Caution: Do not dry or freeze; do not use more than 5% organic solvent. This product is guaranteed for 12 months from the date of arrival.

