

This certificate is an example. A complete certificate containing lot-specific information, such as concentration and volume, will be shipped with your purchase.

PD-Pd Tensidic- blocked (Phosphorescent Nanoparticles)

Catalog No: 15942, 16942

Lot No: Not Available

Chemical Properties:

Contents: 5 ml (Cat # 15941) or 10 ml (Cat # 16941) aqueous suspension of PD-Pd Tensidic-blocked, 0.5 % (w/w) in 10 mM MOPS + 0,5% (w/w) Tween, pH 7, 15 mM sodium azide

Fluorescent Properties:

PD-Particles are based on a novel polymer, which form lattices similar to polystyrene, but with a highly reduced oxygen permeability. Therefore the decay time and the intensity of the incorporated dye-molecules are nearly independent of the oxygen concentration in the sample. In addition the polymer protects the dye from other environmental effects. The particles are less than 100nm. Their surface is carboxy-modified and is blocked with Tween.

PD-Nanoparticles are “loaded” with the Palladium-porphyrin dye, showing a large Stoke's shift . The excellent shielding of the dye against quenchers like oxygen leads to particles with well defined luminescent decay times:

Excitation max: 407, 517, 551 nm

Emission max: 668 nm

Decay-time t: 200 μ s

Delivery-Form: 0.5 % (w/w) in buffer

Quality Control:

The particles have been quality tested by spectro-photometrical evaluation and by determining the solid residue after lyophilization.

Storage:

To ensure stability, the aqueous suspension should be stored at 4°C in the dark.

Caution: Do not dry or freeze; do not use more than 5% organic solvent. This product is guaranteed for 12 months from the date of arrival.

